

PYROSORB-S-M-PU1

Acoustic composite comprising class 'O' acoustic foam faced with flexible polyurethane film.

Product Format: Sheet material or fabricated panels.
Thickness 6 to 60 mm

Product Coding: **PYROSORB-S-M-PU1-25**
(a) **PYROSORB-S** faced with polyurethane film.
(b) Thickness in mm

Properties: Acoustic absorption at mid frequencies.
Acoustic insulation at all frequencies.

Facing properties:

- (1) Durability
- (2) Washability
- (3) Resistance to fungus

Temperature serviceability:

- (a) minimum -30°C
- (b) maximum intermittent 110°C
Continuous 80°C

Flammability:

Composite UL94 V0

BS 476 P7 Class 3

Indicative

Foam UL94 V0

BS 476 P6 Class 1

BS 476 P7 Class 'O'

Usage: Acoustic enclosures in food industry.
Acoustic linings in hostile environments
ie: high humidity & temps

Product Options: **PYROSORB-S-M-PU1-AD** (Self-adhesive)

REF: C141093c replacing C2103902